

ITALIANA® MEMBRANE

PLASTOMERIC MEMBRANES WITH POLYESTER REINFORCEMENT

DATASHEET

DELTAPLAST TNT S

MULTIFUNCTIONAL HYDRO INSULATING MEMBRANES

PRODUCT DESCRIPTION


High quality plastomeric hydro insulating membrane, produced out of destilled bitumen, modified with polypropylene /APP/ additives. The reinforcement is of non-woven polyester, with glass wire. Its bottom surface is covered with easy to be burnt, thin polythene foil, that is melting completely and disappears in the torch's gas flame; its face – with fine quartz sand which prevents the rolled material from adhesion and burning out during the welding.

APPLICATION

Plastomeric membrane, suitable for:

- Bottom layer in multilayered hydro insulating systems for flat roofs;
- Which ever layer in multilayered hydro insulating systems for roof terraces, open to passengers' traffic;
- Singular and double layered systems for bases and underground walls of buildings.

1. Grey mineral slate
2. Modified APP bitumen
3. Non-woven polyester + glass wire
4. Modified APP bitumen
5. Polythene foil



SPECIFIC PROPERTIES OF MODIFIED BITUMINOUS MEMBRANES

- 10 years manufacturer's guarantee;
- Membranes are welded with gas flame burner, at low fuel consumption;
- Perfect adaptation to all kinds of building constructions (concrete, metal, panel, etc.);
- Applicable in residential, public and industrial buildings;
- Harmless to man, no requirements for special means of protection.

PACKING

Palettes, wrapped in polythene foil, with the name of the manufacturer and the basic product data printed on the label.

DIMENSIONS, PRODUCT RANGE AND PACKING

Weight (kg/m2)	Lenght (mm)	Width (mm)	m2 / roll	Number of rolls /palette	m2 / palette
3.00	10	1	10	28	280
3.50	10	1	10	25	250
4.00	10	1	10	23	230
4.50	10	1	10	23	230

TECHNICAL PARAMETERS

Typical Features		Symbol	Value	Unit	Standard
Bitumen		*APP*	Plastomeric	-	-
Reinforcement		*TNT*	Non-woven polyester 150	gr/m²	-
Upper face		*S*	Quartz sand	-	-
Bottom surface		*TF*	Melting foil	-	-
Melting point		t_t	> 145	°C	EN 1427
Flexibility at low temperature		$t_{(-)}$	- 10	°C	EN 1109
Thermal dimensional stability		$t_{(+)}$	> 110	°C	EN 1110
Tensile properties	lengthwise	σ_l	600	N / 5cm	EN 12311 - 1
	crosswise	σ_t	430	N / 5cm	
Break elongation	lengthwise	-	35	%	EN 12311 - 1
	crosswise	-	45	%	
Resistance to static loading	fibre cement	L	15	kg	EN 12730
	polysterol 20 kg/m2 thickness	L	15	kg	
Resistance to impact /polystirol of thickness: 20kg/m2		I	15	*mm*	EN 12691
Water tightness		*W*	Absolute	-	EN 1928
Number of water vapor transmission properties		*μ*	> 20 000	-	EN 1391
Reaction to fire		*E*	Self-extinguishing	-	EN 13501 - 1
Bulgarian Technical Approval		Protocol № 691-05/ 23.03.2005		CRICM, Sofia	EN 13707
Environment Management System		Cer. No. IT 04.1297 / 29.12.2004		SGS, Milano	ISO 14001:2000
Quality Management System		Cer. No. 97.160 / 21.02.2006		SGS, Milano	ISO 9001:2000

Any information contained in this datasheet describes the product properties applicable as at the time of issue. With respect to continuous development of these materials, changes to their properties may take place from time to time.

Address: SIPER-BULGARIA Ltd.
1592 Sofia, P.O. box 150; zh.k."Druzhba 1",
blvd. "Prof.Tsvetan Lazarov" № 50
National phone: /+359 2/ ***0700 19889****; fax: +359 2/****979 00 60***
web page: www.siper.bg; e-mail: office@siper.bg

SIPER