ROCKWOOL®

THERMAL AND FIRESAFE INSULATION

TECHNICAL INSULATION

DATASHEET

WIRED MAT 105 ZINK / RBM

WIRED INSULATION MATS



PRODUCT DESCRIPTION

Mineral wool mats, bonded with organic resin, steel or zinc netting on one side.
Stainless netting is available on request.

APPLICATION

RBM are used for thermal, acoustic and fire-safe insulation of piping, reservoirs, flue gas ducting, industrial equipment, air conditioning, etc., at operating temperatures up to 650 °C, 700 °C, and 750 °C respectively.

SPECIFIC PROPERTIES OF ROCKWOOL STONE WOOL

- Excellent thermal, acoustic and fire-safe qualities;
- Thermal qualities not affected by passing of time;
- Water and moisture repellent, absolute vapour permeability and dimension stability;
- Hydrophobic and non-hygroscopic;
- Chemically neutral;
- Fast and easy to assemble;
- Environmentally friendly, no contents of asbestos or toxic elements;
- Harmless to man, no requirements for special means of protection;
- Not an environment for rodents and micro-organisms.

PACKING

The slabs are wrapped in PE foil with the name of the manufacturer and the basic product data printed on the label.

DIMENSIONS, PRODUCT RANGE AND PACKING							
Thickness (mm)	40	50	60	70	80	90	100
Width (mm)	500						
m^2 / pack	6.00	4.00	3.00	2.50	2.50	2.00	2.00
Number rolls in pack	2	2	2	2	2	2	2

Non standard sizes are available upon agreement with ROCKWOOL, a.s.

TECHICAL PARAMETERS										
Typical features	**Symbol**	**Value**				**Unit**				**Standard**
Density	ρ	~105				kg /m³				EN 1602
Working temperature	t_t	max. 750*				°C				-
Medium thermal resistance at different temperature	t_m	50	100	150	200	250	300	350	°C	EN 12667
	λ_m	0.038	0.042	0.049	0.058	0.068	0.080	0.096	W.m^{-1}.K^{1}	
Reaction to fire	A_1	Non combustible				-				EN 13501-1
Specific heat capacity	C_p	840				J / kg.K				EN 13162
Melting point	t_t	> 1000				°C				DIN 4102
Number of water vapor transmission propertie	μ	1				kg /m³				EN 12086
Noise reduction coefficient α_s	**Hz**	**125**	**250**	**500**		**1000**	**2000**	**4000**		EN ISO 20354
	α_s/ δ = 50mm	0.31	0.82	1.08		1.10	1.08	1.06		
	α_s/ δ = 100mm	0.56	0.83	0.93		0.96	0.88	0.90		
Bulgarian Technical Approval	Protocol № 00-140/ 12.05.2004				SRICM, Sofia					EN 13162
Sanitary Permit	№ 03579 / 2000 by Bulgarian Ministry of Health									
Environment Management System	Certificate No.140868				Bureau Veritas (BVQI) CS Prague					ISO 14001:2000
Quality Management System	Certificate No. 134429				Bureau Veritas (BVQI) CS Prague					ISO 9001:2000

Any information contained in this datasheet describes the product properties applicable as at the time of issue. With respect to continuous development of these materials, changes to their properties may take place from time to time.

Address: SIPER-BULGARIA Ltd.
1592 Sofia, P.O. box 150; zh.k."Druzhba 1",
blvd. "Prof.Tsvetan Lazarov" № 50
*National phone: /+359 2/ **0700 19 889**; fax: **979 00 60***
web page: www.siper.bg; e-mail: office@siper.bg

SIPER